

Qingdao Casting Quality Industrial Co., Ltd.

International Standard

Professional Supplier of Casting Parts

Our manufacture processes:

Sand Casting, Resin Sand Casting
Investment Casting, Lost Wax Casting or Precision Casting
Lost foam casting
Die casting.
CNC Machining.

The material included: cast gray iron, ductile iron, carbon steel, stainless steel, malleable iron, brass alloy and aluminum alloy.

We serve and supply parts, components and products to wide varieties of industries as follow:

1. Valve fittings(valve body, wheel, disc, bonnet and others)
2. Pump Parts (Body, impeller and others)
3. Fastener (Bolt, nut, stud and gasket)
4. Automobile/ Motorcycle (drum, ...)
5. Pipe Fittings(malleable iron fittings, threaded stainless steel fittings, ductile iron fittings and others)
6. Steel anchor products.
7. Food Processing.
8. Computer & communication Hardware.
9. Sporting Equipment.

Tel: +86 532 82972967 Fax: +86 532 82972913



Standard Specification for Steel Castings, Carbon, for General Application¹

This standard is issued under the fixed designation A 27/A 27M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers carbon steel castings for general applications that require up to 70 ksi [485 MPa] minimum tensile strength.

NOTE 1—The grades covered by this specification represent materials that are suitable for assembly with other steel castings or wrought steel parts by fusion welding. It is not intended to imply that all these grades possess the same degree of weldability or that the same welding techniques can be used on all castings. It is the responsibility of the purchaser to establish for himself a suitable welding technique.

1.2 Several grades and two classes of steel castings are covered, as indicated below. The grade and class desired shall be specified by the purchaser.

1.2.1 *Grade N-1*—Chemical analysis only.

1.2.2 *Grade N-2*—Heat-treated but not mechanically tested.

1.2.3 *Grade U-60-30* [415-205]—Mechanically tested but not heat-treated.

1.2.4 *Grades 60-30* [415-205], *65-35* [450-240], *70-36* [485-250], and *70-40* [485-275]—Heat-treated and mechanically tested.

1.2.5 Class 1 and Class 2 steel castings shall be specified in accordance with 9.2.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. Inch-pound units are applicable for material ordered to Specification A 27 and SI units for material ordered to Specification A 27M.

2. Referenced Documents

2.1 *ASTM Standards:*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved April 10, 2003. Published April 2003. Originally approved in 1991. Last previous edition approved in 2000 as A 27/A 27M – 95 (2000).

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

A 732/A 732M Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures³

A 781/A 781M Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use³

3. General Conditions for Delivery

3.1 Material furnished to this specification shall conform to the requirements of Specification A 781/A 781M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A 781/A 781M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 781/A 781M, this specification shall prevail.

4. Ordering Information

4.1 Orders for material under this specification should include the following information in proper sequence.

4.1.1 Quantity,

4.1.2 Specification, grade (1.2), and class (9.2),

4.1.3 Description of the casting by pattern number or drawing,

4.1.4 Options in the specification, and

4.1.5 Supplementary requirements desired, including standards of acceptance.

5. Heat Treatment

5.1 All castings of Grades N-2, 60-30 [415-205], 65-35 [450-240], 70-36 [485-250], and 70-40 [485-275] shall be heat-treated by full annealing, normalizing, normalizing and tempering, or quenching and tempering. Unless otherwise specified in the inquiry, contract, or order, the castings may be heat-treated by any one or combination of these heat-treatments at the option of the manufacturer.

² *Annual Book of ASTM Standards*, Vol 01.03.

³ *Annual Book of ASTM Standards*, Vol 01.02.